

**PRECONTRAI<sup>®</sup> 502**

Technical properties	Precontraint <sup>®</sup> 502	Standards
Yarn	1100 dtex PES HT	Tersuisse
Weight	590 g/sqm	EN ISO 2286-2
Width	180 cm	
Tensile strength (warp/weft)	250/250 daN/ 5 cm	EN ISO 1421
Tear strength (warp/weft)	25/20 daN	DIN 53.363
Adhesion	9/9 daN/ 5 cm	EN ISO 2411
Finish	verniss Biface	
Flame retardancy	<b>M2/NFP 92-507 • B1/DIN 4102-1 • BS 7837 • GROUP 1/AS/NZS 3837 1530.3/AS/NZS • SP METHOD 2205 • M2/UNE 23.727-90 VKF 5.3/SN 198898 • B1/ONORM A 3800-1 • CLASSE 1/UNI 9177-87 METHOD 1/NFPA 701 • CSFM T19 • UBC 31-1 • CLASS A/ASTM E84 G1/GOST 30244-94 • CAN/ULC S109</b>	
Euroclass	<b>B-s2,d0</b>	EN 13501-1
Quality management system		ISO 9001

The technical data here above are average values with a +/- 5% tolerance.

The buyer of our products is fully responsible for their application and their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, use and customs and safety rules of the countries where they are used. Concerning the contractual warranty, please refer to the text of our warranty.

The values here above mentioned are the results of tests performed in conformity with the use and customs in terms of studies; they are given as an indication in order to allow our customers to make the best use of our products. Our products are subject to evolutions due to technical progress; we remain entitled to modify the characteristics of our products at any time. The buyer of our products is responsible to check that the here above data are still valid.